

Marine 2000 SC Rapid



Product description

Marlon Marine 2000 SC Rapid is a cement- based, plastic reinforced screed compound for levelling of all types of subfloor including making slopes in showers, galleys, etc. to be used in all types of dry and wet accommodation areas. For wet accommodation areas, prior to the application of e.g. tiles, the substrate must be treated with a water-resistant membrane (e.g. Marine Elastic 1000 Membrane). Before applying vinyl or carpet, it is recommended that a thin layer of self-levelling compound, such as Marine 900 SL, Marine 1600 SL or Marine 1800 SL is applied to level the floor. By normal condition (20°C/68°F and 80 % RH) Marlon Marine 2000 SC Rapid quickly attains a high surface strength and is walkable after 1 - 3 hours, depending on temperature. Final covering can be applied after approx. 24 hours. Note that the curing time depends on the substrate temperature and the ambient air

Product advantages

For marine and offshore installations of dry and wet accommodation areas before laying carpet, vinyl, tiles etc. and other high traffic areas - mainly foot traffic.

- For most types of substrates
- Rapid drying, fast setting
- Easy to apply
- Low shrinkage
- High surface strength

Surface preparation

The shop-primed surface must be clean, free from dust, grease, oils and other substances, which may impair the adhesion. The whole shop-primed surface must be primed with Marlon Marine Primer F and after the drying of the primer, Marlon Marine 2000 SC Rapid can be applied.

Marlon Marine 2000 SC Rapid cannot be applied directly on zinc-rich shop-primed surfaces, aluminum or galvanized steel. In such case, please contact Marlon Marine.

Mixing process

Marlon Marine 2000 SC Rapid is mixed with cold fresh water to produce a workable screed mortar (amount of water, please see product specification).

Important

The applied Marlon Marine 2000 SC Rapid must not be exposed to freezing temperature, heat, sunlight and draft before being fully cured.

Notice

The recommendations relating to the application and end use of Marlon Marine products are given in good faith based on our current knowledge and experience. The information and recommendations are given without warranty of any kind and does not lead to any further liability for Marlon Marine, besides what is stated in the sales agreement. It is the buyer or end-user's responsibility to investigate or in other way make sure that Marlon Marine's product are suitable for the intended use and further are stored, handled and applied in accordance with stated directions. All orders are delivered and accepted in accordance with Marlon Marine's general conditions of sale.



Product information

Material consumption

1.9 kg/mm/m² (9.87 lb./inch/ft.)

Application temperature

Min. 5-35°C (41-95°F).

Walkable

1-3 hours.

Minimum thickness

15 mm (0.60 in).

Maximum thickness

100 mm (4.0 in) for each layer.

Mixing ratio

2-2.2 liters (67-73 oz) of water per bag of 25 kg (55.12 lb.) 8.5 % of the dry weight of the material.

Pot life

25-30 minutes at 20°C/68°F and 80 % RH.

Shelf-life

Min. 12 months in unopened packaging.

Storage

In dry conditions, do not expose to moisture and freezing temperature.

Packaging

25 kg (55.12 lb) bags on plastic wrapped pallets (42 bags per pallet).

Properties

Compressive strength, 28 days

MPa 34 (4931 psi)

Bending Tear strength, 28 days


MPa 8.2 (1189 psi)

Tested according to FTP Code system and approved according to the IMO Marine Equipment Directives

Method

DS/EN 13892-2

DS/EN 13892-2




Information

Item no.

80325

Version

06.21



A solid solution

